



Udifloor 2024 TAHITI

Report VN710 153926.1
Classification Report



Applicant

JUTEKS d. o. o.
Loznica 53a
3310-Zalec
Slovenia

Reference

Matjaz Prislan

Application

Classification of burning behaviour according to EN 13501-1.

Test material

"Group 17/3"

Material used in testing was anonymized for laboratory purposes. A detailed sample list is contained in the report.

Issuing and Signatures

Number of pages contained: 7
Original Issue / Vienna 15.04.2019 / da2

Authorised for Institute
Ing. Hannes Vittek

A handwritten signature in blue ink, appearing to read 'Vitte', positioned above a horizontal dotted line.

Contents

1	Order	2
1.1	Chronology	2
2	Introduction	3
3	Details of classified building product	3
3.1	General	3
3.2	Description of the building product	3
4	Test reports and test results for the proof of the classification	5
4.1	Test report	5
4.2	Test results	5
5	Classification and field of application	6
5.1	Reference for classification	6
5.2	Classification	6
5.3	Field of application	6
6	Limitations	6
6.1	Notice	6
7	Remarks	7

1 Order

1.1 Chronology

Date	Received	Order
05.04.2019	05.04.2019	Classification of burning behaviour according to EN 13501-1.

2 Introduction

This classification report defines the classification assigned to the building product group “**Group 17/3**” in accordance with the test methods fixed in EN 13501-1.

3 Details of classified building product

3.1 General

The building product group “**Group 17/3**” is defined as flooring, the classification is valid for the end use application described under point 5.3.

3.2 Description of the building product

The building product group „**Group 17/3**“ is defined according EN 14041 as following.

Type	expanded (cushioned) PVC – floor coverings
Dimensions	rolls
Construction	heterogeneous
Surface structure	grained surface
Backing	non-woven secondary backing
Total weight	1330 g/m ² to 2450 g/m ²
Total thickness	2.0 mm to 3.3 mm
Wear layer thickness	0.20 mm to 0.70 mm

The applicant of this classification report guarantees the observance of the instructions for building product groups according EN 14041 as well as the observance of the instructions of the product specification according to EN ISO 26986.

The following articles are part of the building product group “**Group 17/3**”.

Article	Total weight [g/m²]	Total thickness [mm]	Wear layer thickness [mm]
Amiantex	1950	2.9	0.40
Art décor	1330	2.6	0.20
Artex	1330	2.5	0.20
BALANCE	1360	2.5	0.20
BALANCE Blue	1360	2.5	0.20
Blacktex	1940	2.8	0.35
Blacktex HD	1950	2.8	0.40
Blacktex pro	2450	2.5	0.70
Blacktex XL	1950	2.8	0.40
Broadway	1950	2.9	0.40
Cosytex	1550	2.5	0.25
Dantex	1935	2.8	0.35
Dantex 5	1925	2.8	0.35
Evasion	1920	2.8	0.35
Exact	1920	2.8	0.35
Glory	2100	3.3	0.30
Infinity	1950	2.9	0.40
Lifetex	1550	2.5	0.25
Lungo	1950	2.8	0.40
MOONLIGHT	1360	2.5	0.25
NATURE	1810	3.0	0.35
Primatex	1550	2.5	0.25
Protex	2160	3.0	0.55
Puretex	2160	3.0	0.55
Resitex	1950	2.8	0.40
SAFE-TEX	1330	2.5	0.20
SMARTEX	1400	2.0	0.20
SMARTEX PU	1400	2.0	0.20
Soho	1950	2.8	0.40
SUMMERTEX	1700	2.9	0.30
Tessuto	1360	2.5	0.20
Texstar	1950	2.9	0.40
Tex-Style	1700	2.5	0.20
Tex-style	1700	2.5	0.25
Vintage	1950	2.8	0.40

ÖTI - Institut für Ökologie, Technik und Innovation GmbH | Spengergasse 20, 1050 Vienna, Austria

tel +43 1 5442543-0 | fax +43 1 5442543-10 | email office@oeti.at | FN 326826b | VAT No. ATU65149029

UniCredit Bank Austria AG | IBAN AT941200023410378800 | BIC BKAUATWW | EORI ATEOS1000015903

Es gelten ausschließlich unsere Allgemeinen Geschäftsbedingungen | Only our general terms and conditions apply

Member of TESTEX Group

4 Test reports and test results for the proof of the classification

For building product groups preliminary trials with the heaviest/thickest and lightest/thinnest quality have to be carried out (for the most unfavourable case a complete test has to be carried out) respectively the test results of these "border-qualities" are used for the judgement. The classification is done according to the worst case ("BALANCE").

4.1 Test report

Laboratory	ÖTI
Test report number	75197
Date of issue	2015-01-15
Applicant	JUTEKS d.d.
Test methods	EN ISO 11925-2 and EN ISO 9239-1

4.2 Test results

	Test results (Mean Value)	Number of tests
Ignitability, EN ISO 11925-2 Flame spread \leq 150 mm	yes	6
Burning behaviour, EN ISO 9239-1 Critical radiant flux	8.3 kW/m²	3
Integral of smoke obscuration	86 %.min	3

5 Classification and field of application

5.1 Reference for classification

This classification has been carried out in accordance with EN 13501-1.

5.2 Classification

Due to the results of the tests carried out, the building product group "**Group 17/3**" can be classified as following.

Burning behaviour B_{fl}	Smoke emission s1
Classification B_{fl}-s1	

5.3 Field of application

The classification is valid for the building product group described in point 3 under the following end use conditions.

Application	Horizontal laid floor covering in form of rolls
Subfloors	Not burnable subfloors of euroclass A1 _{fl} or A2 _{fl} with a density of at least 1350 kg/m ³ .
Installation	glued
Adhesive	Dispersionsadhesive: "Eurocol 643" (Producer: FORBO) or similar. Note: According to EN 13501-1 the stated classification is valid for the tested floor covering together with the tested adhesive, as well as for all other adhesives of the same generic type as the tested adhesive.

6 Limitations

6.1 Notice

This classification document does not represent type permission or certifying the product.

If a building product should be CE marked according to system 3 of the attestation of conformity systems, the classification stated with this report is suitable as a basis for the declaration of the producer according to the attestation of conformity system 3, together with a CE marking in the context of the directive relating to construction products.

If the manufacturer plans a CE marking in connection with conformity system 3, he has to give an explanation, which has to be attached to the relevant documents. This explanation confirms, that there are no the specific materials, production processes or procedures (e.g. no additives of flame retarding materials, delimitation of organic components or additions of fillers), which are improving the burning behaviour to reach the obtained fire classification. As a consequence from this, the manufacturer drew the conclusion that the system 3 of the attestation of conformity systems is appropriate.

The testing laboratory therefore has played no role in the sampling procedure, although the testing laboratory keeps appropriate references from the manufacturer ready, in order to pursue the examined samples.

7 Remarks

Validity

There are no regulations concerning duration of validity in the individual test standards. As the results of the examinations refer only to the submitted and examined samples, the report is valid for these for an unlimited period. A period of validity specified as part of an expert evaluation is in the discretion of the consultant or the ÖTI.

The applicability of results and expert evaluations for materials not tested is in the responsibility of the applicant. Whereby an apportionment of results as well as any specified period of validity can only be done for identically constructed products and only as long as the product produced unchanged.

Possible national or international restrictions concerning the terms of usability of test and classification reports have to be considered; this is not the responsibility of the test laboratory.

Sample Material

Results of performed tests only refer to the sample material provided.

Without explicit written other agreement testing is destructive and the sample material is transferred to the property of ÖTI, which is entitled to freely decide on storage and disposal.

Issuance

The valid first issue is done in paper and has single-handed signatures. For reference purposes and filing an unsigned electronic duplicate can be delivered in pdf format. Duplicates and translations will be marked accordingly on the cover sheet.

Quality management, Accreditation and Notification

All tests and services are performed under a quality management system according to EN ISO/IEC 17025 respectively EN ISO/IEC 17065.

The ÖTI is accredited as Testing Laboratory and Certification Body for products. It also is a Notified Body for several directives with the registration number 0534 (see <http://ec.europa.eu/enterprise/newapproach/nando/>). Accreditation as Testing Laboratory was provided by Akkreditierung Austria (bmfwf). The scope of accreditation is listed on www.bmfwf.gv.at/akkreditierung.

In this report individual non-accredited test procedures are marked with *.

According to the decree on the use of the accreditation mark ("AkkZV") the accreditation mark is only to be used by the accredited Conformity Assessment Body.

Application of the registration number of the Notified Body: As to personal protective equipment (PPE) the requirements of PSA-SV § 10, BGBl. Nr. 596/1994 as amended and article 13 of the Directive 89/686/EEC have to be kept. With construction products the application is only permitted within the declaration of performance for CE-marking.

Copyright and Usage Notes

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents.

Reports are protected under international copyright laws. Written consent of the ÖTI is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.

End of report